

Technical Data Sheet
Malen E FGNX 23-D022
Low Density Polyethylene



Product Description

Malen E FGNX 23-D022 is a non-additivated, low density polyethylene. It is suitable for manufacture transparent films, which exhibit very good mechanical properties and are notable for their high transparency and gloss. It is delivered in pellet form.

This product may not be used in medical and pharmaceutical applications.

Regulatory Status

For regulatory compliance information, see **Malen E FGNX 23-D022 [Data Sheet of Compliance and Safety Data Sheet](#)**.

Status	Commercial: Active
Availability	Europe
Processing Method	Blown Film, CAST film
Features	Good Optical Properties, Good Processability, Good Heat Seal
Market / Applications	Flexible Packaging / Bags & Pouches; Food Packaging Film; Hygiene Film; Shrink Film Recommended Film Thickness: 25 - 100 µm

Typical Properties	Value	Unit	Method
Physical			
Density	0.923	g/cm ³	PN EN ISO 1183-1
Melt flow rate (MFR); (190°C/2,16 kg)	1.95	g/10 min	PN EN ISO 1133
Mechanical			
Tensile Modulus	230	MPa	PN EN ISO 527-1, 2
Tensile Stress at Yield	10.0	MPa	PN EN ISO 527-1, 2
Film			
Tensile Strength			
- MD	20.0	MPa	PN EN ISO 527-1, 3
- TD	19.0	MPa	PN EN ISO 527-1, 3
Tensile Strain at Break			
- MD	370	%	PN EN ISO 527-1, 3
- TD	500	%	PN EN ISO 527-1, 3
Dart Drop Index	190	g	PN EN ISO 7765-1
Coefficient of Friction	0.60	-	PN EN ISO 8295
Gloss	65	-	ASTM D 2457
Haze	8	%	ASTM D 1003
Hardness			
Shore hardness (Shore D)	50		PN EN ISO 868
Thermal			
Vicat softening temperature (A50; 50°C/h 10N)	90	°C	PN EN ISO 306
Melting Temperature	111	°C	PN EN ISO 11357-3
Processing Parameters			
Extrusion Temperature	170-220	°C	

Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 180°C and a blow-up ratio of 1:2.5.

Notes: These are typical property values not to be construed as specification limits.

Further Information

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

In cases where higher temperatures are required, please contact your appropriate technical contact for support.

Health and Safety

The resin is manufactured to the highest standards, but special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off-line operations. The products of degradation may have an unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapours. Legislation on the control of emissions and pollution prevention should be observed.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. While burning, the resin contributes high heat and may generate a dense black smoke.

Recycled resins may have previously been used as packaging for, or may have otherwise been in contact with, hazardous goods. Converters are responsible for taking all necessary precautions to ensure that recycled resins are safe for continued use.

For further information about safety in handling and processing please refer to the Safety Data Sheet.

Conveying

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks.

Storage

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i.e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavourable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Company Information

For further information regarding the LyondellBasell company, please visit www.basellorlen.pl/.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a Basell Orlen Polyolefins Sp. z o.o. representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.